

MATERIAL SAFETY DATA SHEET

DATE: 5-16-06

INTERMIX SYSTEM

SECTION 1 - MANUFACTURER

Manufacturer: PRO-SPRAY
An Alco Industries Company
 600 Nova Drive SE
 Massillon, Ohio 44646
 Phone: 330-830-6000
 Fax: 330-830-6005

FOR CHEMICAL EMERGENCY

CHEMTREC: 1-800-424-9300
 CANUTEC: 1-613-996-6666
 (For Canada Call Collect)

Hazardous Materials Information: See Section 10

DOT Shipping Name: Paint, 3 UN1263 PG III
OSHA Hazard Class: Flammable Liquid

SECTION 2 – HAZARDOUS INGREDIENTS (see section 10)

HAZARDOUS INGREDIENT	EMERG. PLAN*	NOTE	CAS NO	ACGIH TLV ppm	OSHA PEL ppm	STEL* ppm	HMIS* H-F-R	FLASH POINT T.C.C./F	VAPOR PRESSURE mm/Hg.
2,4, PENTANEDIONE	YES		123-54-6	20	20		3-3-1	96	6.8 @68°F
2-BUTOXYETHYL ACETATE	NO		112-07-02	N/E	N/E	N/E	2-2-0	160	0.2 @ 68°F
2-BUTOXYETHYL ACETATE	NO		112-07-02	N/E	N/E		2-2-0	160	0.3 @68°F
ACETONE	YES		67-64-1	750	750	1000	1-3-0	<-1.0	182 @68°F
ACRYLIC POLYMER A	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A
ALUMINIUM HYDROXIDE	NO								
ALUMINUM	NO		7429-90-5	10	5	N/E	N/E	N/A	N/A
AMORPHOUS SILICA	NO		7631-86-9	N/E	N/E	N/E	N/E	N/A	N/A
ANTIMONY OXIDE	NO								
AROMATIC HYDROCARBONS	NO		64742-95-6	50	50	150	1-3-0	110	4 @ 68°F
AROMATIC HYDROCARBONS	NO		64742-95-6	50	50	150	1-3-0	110	3 @68°F
BARIUM SULFATE	NO		7727-43-7	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIG YELLOW 34 (LEAD SULFOCHROMATE)	YES	4	1344-37-2	0.05 (mg/m3)	0.012 (mg/m3)		2-2-0	N/A	N/A
C.I PIGMENT BLUE 15	NO		68987-63-3	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT BISMUTH VANADIUM OXIDE	NO		14059-33-7	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT BROWN 25	NO		6992-11-6	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT GREEN 7	NO		1328-53-6	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT YELLOW	NO		15680-42-9	5	10	N/E	N/E	N/A	N/A
C.I PIGMENT YELLOW 42	NO		51274-00-1	5	10	N/E	N/E	N/A	N/A
C.I PIGMENT YELLOW 110	NO		106276-80-6	5	10	N/E	N/E	N/A	N/A
C.I PIGMENT RED 175	NO		6985-92-8	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT RED 179	NO		5521-31-3	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT RED 254	NO		84632-65-5	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT RED 224	NO		128-69-8	N/E	N/E	N/E	N/E	N/A	N/A
C.I PIGMENT QUINACRIDONE RED	NO		1047-16-1	N/E	N/E	N/E	N/E	N/A	N/A
C.I. PIG RED 104 (LEAD MOLBDATE/CHROMATE/SULFATE)	YES	4	12656-85-8	0.05 (mg/m3)	0.012 (mg/m3)		2-2-0	N/A	N/A
CALCIUM CARBONATE	NO		471-34-1	N/E	N/E	N/E	N/E	N/A	N/A
CARBAZOLE VIOLET	NO		6358-30-1	N/E	N/E	N/E	N/E	N/A	N/A
CARBON BLACK	NO		1333-86-4	3.5 (mg/m3)	3.5 (mg/m3)		N/A	N/A	N/A
GRAPHITE	NO		7782-42-5	N/E	N/E	N/E	N/E	N/A	N/A
CELLULOSE ACETATE BUTYRATE	NO		9004-36-8	N/E	N/E	N/E	N/E	N/A	N/A
CHROMIC OXIDE	YES		18282-10-5	0.5	0.5		2-2-0	N/A	N/A
CHROMIUM HYDROXIDE	NO		1308-14-1	N/E	N/E	N/E	N/E	N/A	N/A
DIISOBUTYL KETONE	NO		108-83-8	25	25	N/E	2-2-0	120	1.7 @68°F
ETHYL 3-ETHOXY PROPINATE	YES		763-69-9	N/E	N/E	100	1-2-0	136	1.5 @ 77°F
ETHYL 3-ETHOXY PROPINATE	YES		763-69-9	N/E	N/E	100	1-2-0	136	1.5 @68°F
ETHYL ACETATE	YES		141-78-6	400	400	N/E	1-3-0	24	86 @ 68°F
ETHYL ACETATE	YES		141-78-6	400	400	N/E	1-3-0	24	86 @68°F
ETHYL BENZENE	YES		100-41-4	100	100				7.10@68°F
ETHYL BENZENE	NO	1	100-41-4	100	100	150	2-3-0	77	7.10 @68°F
ETHYLENE GLYCOL N-BUTYL ETHER	NO		111-76-2	N/E	N/E		1-2-0	165	.88 @77°F
HEPTYL ACETATE	NO		90438-79-2	N/E	N/E		1-2-0	151	1 @68°F
HEXYL ACETATE	NO		88230-35-7	N/E	N/E		1-2-0	135	1.4 @68°F

HYDROXY ACRYLIC RESIN A	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A
HYDROXY ACRYLIC RESIN B	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A
HYDROXY ACRYLIC RESIN C	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A
INDANTHRONE BLUE	NO		81-77-6	N/E	N/E	N/E	N/E	N/A	N/A
IRON HYDROXIDE OXIDE	NO								
IRON OXIDE	NO		1309-37-1	N/E	N/E	N/E	N/E	N/A	N/A
IRON OXIDE	NO		1309-37-1	5	10	N/E	N/E	N/A	N/A
ISOBUTYL ACETATE	NO		110-19-0	150	150	187	1-3-0	62	14.8 @68°F
ISOBUTYL ALCOHOL	NO		78-83-1	N/E	N/E		2-2-0	85	8.8 @68°F
ISOPROPYL ALCOHOL	YES		67-63-0	400	400	500	1-3-0	53	32 @68°F
METHYL ALCOHOL	NO		67-56-1	200	200		2-2-0	54	97 @68°F
METHYL AMYL KETONE	NO		110-43-0	50	100	N/E	1-2-0	102	2.1 @68°F
METHYL ETHYL KETONE	YES		78-93-3	200	200	300	3-3-0	16	85 @68°F
METHYL ISOBUTYL KETONE	YES		108-10-1	50	50	75	2-3-0	60	16 @68°F
METHYL PROPYL KETONE	NO		107-87-9	200	200	250	2-3-0	46	27 @68°F
METHYL PROPYL KETONE	NO		107-87-9	200	200		1-2-0	45	27 @68°F
MICA (MINERAL)	NO		12001-26-2	3	3	3	N/A	N/A	N/A
MINERAL SPIRITS	NO		8032-32-4	100	100	100	1-2-0	100	<1 @68°F
MONOAZO ORANGE	NO		12236-62-3	N/E	N/E	N/E	N/E	N/A	N/A
N-BUTYL ACETATE	YES		123-86-4	150	150	200	2-3-0	81	10 @ 68°F
N-BUTYL ALCOHOL	YES		71-36-3	50	50	N/E	2-3-0	97	5.5 @68°F
N-HEPTANE	NO		142-82-5	400	400		1-3-0	20	60 @77°F
NYLON	NO		25038-74-8	N/E	N/E	N/E	N/A	N/A	N/A
PETROLEUM NAPHTHA	NO		8032-32-4	300	300	N/E	2-3-0		3.4 @ 68°F
PHthalocyanine BLUE	NO		147-14-8	N/E	N/E	N/E	N/E	N/A	N/A
PROPIONIC ACID	NO		590-01-2	N/E	N/E	N/E	2-2-0	100	3.4 @68°F
POLYESTER RESIN A	NO		N/A	N/E	N/E	N/E	N/A	N/A	N/A
PROPYLENE GLYCOL MONOMETHYL ETHER	YES		107-98-2	100	100		2-3-0	94 OPEN CUP	11 @77°F
PROPYLENE GLYCOL MONOMETHYL ETHER ACETATE	NO		108-65-6	N/E	N/E	N/E	2-3-0	114 SETA CLOSED	2.4 @ 68°F
QUINACRIDONE	NO		1047-16-1	N/E	N/E	N/E	N/E	N/A	N/A
SILICA	NO		7631-86-9	10	5	N/E	N/A	N/A	N/A
SOLVENT NAPHTHA (PETROLEUM), LIGHT AROMATIC	NO		64742-95-6	100	100	N/E	2-3-0	110	4@68°F
STRONTIUM CHROMATE	YES	3	7789-06-2				4-0-0	N/A	N/A
STYRENE	YES		100-42-5	100	100	100	2-3-2	88	4.5 @68°F
TITANIUM DIOXIDE	NO		13463-67-7	N/E	N/E		0-0-0	N/A	N/A
TOLUENE	YES	3	108-88-3	50	100	150	2-3-0	45	47 @ 68°F
VM&P NAPHTHA	NO		64742-89-8	N/E	N/E		1-3-0	18	38 @68°F
XYLENE	YES	1	1330-20-7	100	100	150	2-3-0	80	9.5 @68°F
YELLOW BENZIMIDAZOLONE	NO		68134-22-5	N/E	N/E	N/E	N/A	N/A	N/A
ZINC TETROXY CHROMATE	YES	3	13530-65-9	N/E	N/E		3-3-0	N/A	N/A

SECTION 3 – PHYSICAL DATA

Evaporation rate: Less than ether

Solubility in water: 0.1%

Percentage volatile by weight: 20.00 – 50.0%

Gallon weight: 8.00 – 13.15 lb/gallon

Vapor density: Heavier than air

Percent volatile by volume: 30% - 40.00%

Boiling range: 54 °C - 245°C/129°F-473°F

SECTION 4 – FIRE & EXPLOSION DATA

Flash point (closed cup): See section 10 for exact values

Flammable limits: 0.8% - 19.9%

Extinguishing media: Water spray, foam, carbon dioxide, and dry chemical.

Special fire fighting procedures: Full protective equipment, including self-contained breathing apparatus is recommended. Water from fog nozzles may be used to cool closed containers to prevent pressure build up.

Unusual fire & explosion hazards: When heated above the flash point, emits flammable vapors which, when mixed with air, can burn or be explosive. Fine mists or sprays may be flammable at temperatures below the flash point.

SECTION 5 – HEALTH HAZARD DATA

General Effects:

Ingestion: Gastro-intestinal distress. In the unlikely event of ingestion, call a physician immediately and have the names of the ingredients available.

Inhalation: May cause nose and throat irritation. May cause nervous system depression characterized by the following progressive steps: Headache, dizziness, nausea, staggering gait, confusion, and/or unconsciousness. **Toluene** has been found by the state of California to cause birth defects and other reproductive harm. **Propylene glycol Monomethyl ether acetate** and **n-Butyl alcohol** may cause moderate eye burning and can be absorbed through the skin in harmful amounts. Laboratory studies with rats have shown that petroleum distillates cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs, or monkeys. Several studies evaluating petroleum workers have not shown significant increases of kidney damage or kidney or liver tumors. Extremely high concentration of n-butyl acetate has caused blood changes and weakness in laboratory animals. Repeated extremely high exposures of laboratory animals to **Ethyl acetate** resulted in secondary anemia with and increase in white blood cells, fatty degeneration, cloudy swelling, and an excess of blood in various organs. **Dibasic ester** inhalation overexposure in rats has shown mild injury to the olfactory region of the nose. **Strontium Chromate** is a NTP and IARC listed carcinogen. **Ethylene glycol monobutyl ether acetate** can be absorbed through the skin in harmful amounts. In studies in laboratory animals has produced damage to red blood cells and kidneys. Reports have associated repeated and prolonged overexposure to solvents with permanent brain and nervous system damage. If affected by inhalation of vapor or spray mist, remove to fresh air. If breathing difficulty persists, or occurs later, consult a physician.

Skin or eye contact: Repeated or prolonged liquid contact may cause skin irritation with discomfort and dermatitis. In case of eye contact, immediately flush with plenty of water for at least 15 minutes; and call a physician. In case of skin contact, wash with soap and water. If irritation occurs, contact a physician.

Skin or eye contact: May cause irritation or burning of the eyes. Repeated or prolongs liquid contact may cause skin irritation with discomfort and dermatitis. In case of eye contact, immediately flush with plenty of water for at least 15 minutes; call a physician. In case of skin contact, wash with soap and water. If irritation occurs, contact a doctor.

Special Effects:

Aromatic hydrocarbon A, B; VM&P Naphtha – laboratory studies with rats have shown that petroleum distillates cause kidney damage and kidney or liver tumors. These effects were not seen in similar studies with guinea pigs, dogs or monkeys. Several studies evaluating petroleum workers have not shown a significant increase of kidney damage or an increase in kidney or liver tumors.

Butyl acetate – may cause abnormal liver function. Tests for embryotoxic activity in animals has been conclusive. Has been toxic to the fetus in laboratory animals at doses that are toxic to the mother.

Melamine resin – This chemical is a formaldehyde donor. Formaldehyde is an IARC, NTP or OSHA carcinogen and has shown mutagenic activity in laboratory cell culture tests. Formaldehyde has produced tumors in the nasal passage of laboratory animals when exposed to high concentrations for a two-year period. Epidemiology studies conducted to date have not found evidence of formaldehyde related tumor induction in humans.

Warning: This chemical is known to the State of California to cause cancer.

Methyl ethyl ketone – High concentrations have caused embryotoxic effects in laboratory animals. Methyl ethyl ketone has been demonstrated to potentiate (i.e., shorten the time of onset) the peripheral neuropathy caused by either n-hexane or methyl n-butyl ketone. MEK by itself has not been demonstrated to cause peripheral neuropathy. Liquid splashes in the eye may result in chemical burns.

Titanium dioxide - In a lifetime inhalation test, lung cancers were found in some rats exposed to 250-mg/m³ respirable titanium dust. Analysis of the titanium dioxide concentrations in the rat's lungs showed that the lung clearance mechanism was overwhelmed and that the results at the massive 250-mg/m³ levels are not relevant to the workplace.

Toluene – Recurrent overexposure may result in liver and kidney injury. High airborne levels have produced irregular heartbeat in animals and occasional palpitations in humans. Rats exposed to very high airborne levels have exhibited high frequency hearing defects. The significance of this to man is unknown.

Warning: This chemical is known to the State of California to cause birth defects or other reproductive harm.

Xylene – High concentrations have caused embryotoxic effects in laboratory animals. Recurrent overexposure may result in liver and kidney injury. Can be absorbed through the skin in harmful amounts.

Formaldehyde – repeated exposure may cause allergic skin rash, itching, swelling. Causes severe eye irritation. Formaldehyde has produced tumors in the nasal passage of laboratory animals when exposed to high concentrations for a two-year period. Epidemiology studies conducted to date have not found evidence of formaldehyde related tumor induction in humans. May induce pulmonary sensitization or significant irritation of the respiratory airways. Is an IRAC, NTP or OSHA carcinogen? Has shown mutagenic activity in laboratory cell culture tests.

Warning: This chemical is known to the State of California to cause cancer.

SECTION 6 – REACTIVITY DATA

Stability: Stable

Incompatibility (materials to avoid): None reasonably foreseeable

Hazardous decomposition products: CO, CO₂, smoke

Hazardous polymerization: Will not occur

SECTION 7 – SPILL OR LEAK PROCEDURES

STEPS TO BE TAKEN IN CASE MATERIAL IS RELEASED OR SPILLED: Provide maximum ventilation. Only personnel equipped with proper respiratory, skin, and eye protection should be permitted in the area. Remove all sources of ignition. Take up spilled material with sand, vermiculite, or other non-combustible absorbent material and place in clean, empty containers for disposal. Only the spilled material and the absorbent should be placed in this container.

WASTE DISPOSAL METHOD: Waste material must be disposed of in accordance with federal, state, provincial, and local environmental control regulations. Empty containers should be recycled or disposed of through an approved waste management facility.

SECTION 8 – SPECIAL PRECAUTIONS

Precautions to be taken in handling and storing: Observe label precautions. Keep away from heat, sparks, and flame. Close container after each use. Ground containers when pouring. Wash thoroughly after handling and before eating or smoking. Do not store above 120°F.

Other precautions: DO NOT sand, flame cut, braze or weld dry coating without a NIOSH/MSHA approved respirator or appropriate ventilation.

* Subject to the reporting requirements of section 313 of the Emergency Planning and Community right to know act of 1986 and 40CFR372.

** Short-term exposure limit

Note 1 - Xylene contains 18-20% Ethyl Benzene (CAS# 100-41-4) having a PEL of 100 ppm, TLV of 100 ppm and a STEL of 150 ppm.

Note 2 - Toluene is known to the state of California to cause birth defects or other reproductive harm.

Note 3 - Zinc Tetraoxy Chromate and Strontium Chromate are NTP and IARC listed carcinogens.

N/E - Not established as reported by manufacturer.

Respiratory: DO NOT breathe vapors or mists. When this product is used with a pint requiring isocyanate hardener or activator, wear a continuous flow supplied air respirator (NIOSH/MSHA TC-19C approved) when mixing the hardener/activator with the paint, during application and until all vapor and spray mists are exhausted. DO NOT permit anyone without respirator protection in the painting area. Refer to the hardener/activator label instructions and MSDS for further information. Follow the respirator manufacturer's directions for respirator use.

Ventilation: Provide sufficient ventilation in volume and pattern to keep contaminants below applicable OSHA requirements.

Protective clothing: Neoprene gloves and coveralls are recommended.

Eye protection: Desirable in all industrial situations. Include splashguards or side shields.

SECTION 10 – OTHER INFORMATION

Section 313 Supplier Notification: The chemicals listed below with percentages are subject to the reporting requirements of Section 313 of the Emergency Planning and Right-To-Know Act of 1986 and of 40 CFR 372.

~ NFPA ratings for individual products have not been established. The ratings given are the highest rating of any ingredient contained in that product.

NOTICE: The data in this Material Safety Data Sheet relate only to the specific material designated herein and do not relate to use in combination with another material or in any process.

Product Code: Pro-Spray MB-201-2 PALE WHITE MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (10%), ethyl benzene, Titanium Dioxide (1-5%)

Gallon Weight:	8.17	Boiling Range:	259-418
% Solids by Weight:	48.96	H: 2 F: 3 R: 0	
% Solids by Volume:	41.82	Flash Point:	70°F
V.O.C.:	4.17 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-203-2 TRANSPARENT BLACK MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (10%), ethyl benzene, Carbon Black (0.1-1.0%)

Gallon Weight:	8.02	Boiling Range:	259-418
% Solids by Weight:	47.89	H: 2 F: 3 R: 0	
% Solids by Volume:	42.44	Flash Point:	70°F
V.O.C.:	4.18 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-204-3 YELLOW OXIDE MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), Iron Hydroxide Oxide (10-20%)

Gallon Weight:	8.77	Boiling Range:	259-418
% Solids by Weight:	52.23	H: 2 F: 3 R: 0	
% Solids by Volume:	42.50	Flash Point:	70°F
V.O.C.:	4.19 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-206-3 RED OXIDE MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), Iron Oxide (10-20%)

Gallon Weight:	8.91	Boiling Range:	259-418
% Solids by Weight:	53.65	H: 2 F: 3 R: 0	
% Solids by Volume:	43.26	Flash Point:	70°F
V.O.C.:	4.13 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-207-2 RUSSET MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), Iron Oxide (1-5 %)

Gallon Weight:	8.09	Boiling Range:	259-418
% Solids by Weight:	48.46	H: 2 F: 3 R: 0	
% Solids by Volume:	41.91	Flash Point:	70°F
V.O.C.:	4.17 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-209-2 DEEP BLUE MS TINTER

Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), Phthalocyanine Blue (0.1-1.0%).

Gallon Weight:	8.02	Boiling Range:	259-418
% Solids by Weight:	48.26	H: 2 F: 3 R: 0	
% Solids by Volume:	42.06	Flash Point:	70°F
V.O.C.:	4.15 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-215-2 MEDIUM YELLOW MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), Iron Hydroxide Oxide (0.1-1.0%)

Gallon Weight:	8.03	Boiling Range:	259-418
% Solids by Weight:	48.07	H: 2 F: 3 R: 0	
% Solids by Volume:	42.78	Flash Point:	70°F
V.O.C.:	4.17 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-219-2 VIOLET MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), Carbazole Violet (1-5%)

Gallon Weight:	8.00	Boiling Range:	259-418
% Solids by Weight:	44.25	H: 2 F: 3 R: 0	
% Solids by Volume:	38.60	Flash Point:	70°F
V.O.C.:	4.46 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-224-2 SUPER RED MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), Ci Red 168

Gallon Weight:	8.05	Boiling Range:	259-418
% Solids by Weight:	46.22	H: 2 F: 3 R: 0	
% Solids by Volume:	39.83	Flash Point:	70°F
V.O.C.:	4.33 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-229-3 BLUE LAKE MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%), Indanthrone Blue (5-10%).

Gallon Weight:	8.09	Boiling Range:	259-418
% Solids by Weight:	44.39	H: 2 F: 3 R: 0	
% Solids by Volume:	39.15	Flash Point:	70°F
V.O.C.:	4.39 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-231-3 BLUE BLACK MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%), Carbon Black (1-5%).

Gallon Weight:	8.04	Boiling Range:	259-418
% Solids by Weight:	47.39	H: 2 F: 3 R: 0	
% Solids by Volume:	41.51	Flash Point:	70°F
V.O.C.:	4.23 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-237-2 TONE CONTROLLER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%), Silica (10-20%)

Gallon Weight:	8.67	Boiling Range:	259-418
% Solids by Weight:	51.32	H: 2 F: 3 R: 0	
% Solids by Volume:	42.22	Flash Point:	70°F
V.O.C.:	4.22 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-240-2 TRANSOXIDE RED MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%), Iron Oxide (10-20%)

Gallon Weight:	9.07	Boiling Range:	259-418
% Solids by Weight:	52.34	H: 2 F: 3 R: 0	
% Solids by Volume:	41.07	Flash Point:	70°F
V.O.C.:	4.23 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-251-2 FAST BLUE MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%) Phthalocyanine Blue (5-10%)

Gallon Weight:	8.07	Boiling Range:	259-418
% Solids by Weight:	44.60	H: 2 F: 3 R: 0	
% Solids by Volume:	38.40	Flash Point:	70°F
V.O.C.:	4.47 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-259-2 BURGUNDY MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%).

Gallon Weight:	8.02	Boiling Range:	259-418
% Solids by Weight:	53.30	H: 2 F: 3 R: 0	
% Solids by Volume:	42.32	Flash Point:	70°F
V.O.C.:	4.17 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-265-2 WINE RED MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%) c.i. Red 175 (10-20%).

Gallon Weight:	8.09	Boiling Range:	259-418
% Solids by Weight:	46.00	H: 2 F: 3 R: 0	
% Solids by Volume:	36.63	Flash Point:	70°F
V.O.C.:	4.62 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-272-2 CYAN BLUE MS TINTER

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%) Phthalocyanine Blue (5-10%)

Gallon Weight:	8.08	Boiling Range:	259-418
% Solids by Weight:	45.04	H: 2 F: 3 R: 0	
% Solids by Volume:	39.38	Flash Point:	70°F
V.O.C.:	4.44 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-273 –2 BRONZE GREEN

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%) Yellow pigment (10-20%).

Gallon Weight:	8.07	Boiling Range:	259-418
% Solids by Weight:	46.11	H: 2 F: 3 R: 0	
% Solids by Volume:	39.61	Flash Point:	70°F
V.O.C.:	4.52 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-275-2 STRONG MAROON

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%), pigment red 179 (5-10%).

Gallon Weight:	8.14	Boiling Range:	259-418
% Solids by Weight:	44.42	H: 2 F: 3 R: 0	
% Solids by Volume:	37.09	Flash Point:	70°F
V.O.C.:	4.54 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-276-2 BROWN

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%), c.i. pigment brown 25 (5-10%).

Gallon Weight:	8.04	Boiling Range:	259-418
% Solids by Weight:	45.93	H: 2 F: 3 R: 0	
% Solids by Volume:	39.13	Flash Point:	70°F
V.O.C.:	4.38 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-277-2 FAST MAROON

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%), pigment quinacridone red (5-10%).

Gallon Weight:	8.12	Boiling Range:	259-418
% Solids by Weight:	45.38	H: 2 F: 3 R: 0	
% Solids by Volume:	39.25	Flash Point:	70°F
V.O.C.:	4.40 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-278-2 TRANSOXIDE YELLOW

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%), c.i pigment yellow 42 (10-20%).

Gallon Weight:	9.06	Boiling Range:	259-418
% Solids by Weight:	53.73	H: 2 F: 3 R: 0	
% Solids by Volume:	42.84	Flash Point:	70°F
V.O.C.:	4.24 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray MB-279-2 STRONG YELLOW

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%), c.i pigment yellow 110 (10-20%)

Gallon Weight:	8.21	Boiling Range:	259-418
% Solids by Weight:	42.50	H: 2 F: 3 R: 0	
% Solids by Volume:	33.29	Flash Point:	70°F
V.O.C:	4.77 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray HB-500-3 H.S. SUPER WHITE

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (10%), Titanium Dioxide (20-30%), silica, aluminium hydroxide.

Gallon Weight:	10.88	Boiling Range:	259-418
% Solids by Weight:	64.06	H: 2 F: 3 R: 0	
% Solids by Volume:	53.00	Flash Point:	70°F
V.O.C:	4.02 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray HB-511-2 H.S. CLARET

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), Quinacridone (5-10%)

Gallon Weight:	8.11	Boiling Range:	259-418
% Solids by Weight:	44.25	H: 2 F: 3 R: 0	
% Solids by Volume:	37.53	Flash Point:	70°F
V.O.C:	4.53 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray HB-512-2 H.S. LAGOON BLUE

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), C.I Pigment Blue (5-10%)

Gallon Weight:	8.16	Boiling Range:	259-418
% Solids by Weight:	44.25	H: 2 F: 3 R: 0	
% Solids by Volume:	38.36	Flash Point:	70°F
V.O.C:	4.38 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray HB-520-3 H.S. ORANGE

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (10%), Silica (1-5%), Ci Pigment Red 104 (30-40%), antimony oxide,

Gallon Weight:	11.16	Boiling Range:	259-418
% Solids by Weight:	63.45	H: 2 F: 3 R: 0	
% Solids by Volume:	43.12	Flash Point:	70°F
V.O.C:	4.08 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray HB-523-2 H.S. BRIGHT YELLOW

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (5-10%), Lead Chromate-Lead Sulfate (30-40%), Silica, Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic,

Gallon Weight:	11.48	Boiling Range:	259-418
% Solids by Weight:	63.77	H: 2 F: 3 R: 0	
% Solids by Volume:	41.46	Flash Point:	70°F
V.O.C:	4.16 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray HB-525-2 H.S. SUN YELLOW

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (5-10%), Lead Chromate-Lead Sulfate (30-40%), Silica, Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic,

Gallon Weight:	10.94	Boiling Range:	259-418
% Solids by Weight:	62.89	H: 2 F: 3 R: 0	
% Solids by Volume:	41.88	Flash Point:	70°F
V.O.C:	4.06 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray HB-545-3 H.S. STRONG RED

Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (5-10%), Pigment Red 254 (10-20%)

Gallon Weight:	8.44	Boiling Range:	259-418
% Solids by Weight:	45.64	H: 2 F: 3 R: 0	
% Solids by Volume:	44.89	Flash Point:	70°F
V.O.C:	4.03	OSHA Storage:	1B

Product Code: Pro-Spray HB-546-2, HB-546-3 H.S. BLACK

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Carbon Black (1-5%).

Gallon Weight:	8.11	Boiling Range:	259-418
% Solids by Weight:	46.98	H: 2 F: 3 R: 0	
% Solids by Volume:	40.46	Flash Point:	70°F
V.O.C:	4.30 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray HB-547-2, HB-547-3 H.S. JET BLACK

Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (5-10%), Carbon Black (1-5%)

Gallon Weight:	8.24	Boiling Range:	259-418
% Solids by Weight:	45.64	H: 2 F: 3 R: 0	
% Solids by Volume:	35.11	Flash Point:	70°F
V.O.C:	4.48 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray HB-551-2 H.S. BLUE GREEN

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (10-20%), C.i Pigment Green 7 (10-20%).

Gallon Weight:	8.42	Boiling Range:	259-418
% Solids by Weight:	45.97	H: 2 F: 3 R: 0	
% Solids by Volume:	36.78	Flash Point:	70°F
V.O.C:	4.55 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray HB-552-2 H.S. FAST BLUE

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (5-10%), Phthalocyanine Blue 15 (5-10%)

Gallon Weight:	8.25	Boiling Range:	259-418
% Solids by Weight:	47.88	H: 2 F: 3 R: 0	
% Solids by Volume:	40.34	Flash Point:	70°F
V.O.C.:	4.30 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray HB-570-2 H.S. BRILLIANT RED

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (5-10%), c.i. pigment red 254 (1-5%)

Gallon Weight:	8.19	Boiling Range:	259-418
% Solids by Weight:	48.44	H: 2 F: 3 R: 0	
% Solids by Volume:	39.28	Flash Point:	70°F
V.O.C.:	4.34 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray AB-810-2 H.S. BRIGHT MEDIUM ALUMINIUM

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, 1-methoxy-2-propyl acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight:	8.11	Boiling Range:	259-428
% Solids by Weight:	26.64	H: 2 F: 3 R: 0	
% Solids by Volume:	20.66	Flash Point:	79°F
V.O.C.:	5.95 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray AB-814-2 H.S. FINE ALUMINIUM

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, 1-methoxy-2-propyl acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight:	8.05	Boiling Range:	259-428
% Solids by Weight:	26.22	H: 2 F: 3 R: 0	
% Solids by Volume:	20.94	Flash Point:	70°F
V.O.C.:	5.94 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray AB-816-3 H.S. MEDIUM ALUMINIUM

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, 1-methoxy-2-propyl acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight:	8.07	Boiling Range:	259-428
% Solids by Weight:	26.65	H: 2 F: 3 R: 0	
% Solids by Volume:	21.00	Flash Point:	70°F
V.O.C.:	5.92 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray AB-818-3 H.S. MEDIUM COARSE ALUMINIUM

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, 1-methoxy-2-propyl acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight:	8.08	Boiling Range:	259-428
% Solids by Weight:	26.65	H: 2 F: 3 R: 0	
% Solids by Volume:	21.00	Flash Point:	70°F
V.O.C.:	5.92 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray AB-821-2 H.S. COARSE ALUMINIUM

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, 1-methoxy-2-propyl acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight:	8.07	Boiling Range:	259-428
% Solids by Weight:	26.65	H: 2 F: 3 R: 0	
% Solids by Volume:	21.00	Flash Point:	70°F
V.O.C.:	5.92 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray AB-832-2 H.S. VERY COARSE ALUMINIUM

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, 1-methoxy-2-propyl acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight:	7.99	Boiling Range:	259-428
% Solids by Weight:	24.41	H: 2 F: 3 R: 0	
% Solids by Volume:	20.29	Flash Point:	70°F
V.O.C.:	6.04 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray AB-838-2 H.S. BRIGHT MEDIUM ALUMINIUM

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, 1-methoxy-2-propyl acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight:	8.16	Boiling Range:	259-428
% Solids by Weight:	27.46	H: 2 F: 3 R: 0	
% Solids by Volume:	27.80	Flash Point:	70°F
V.O.C.:	5.92 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray AB-841-2 SHINING COARSE ALUMINIUM

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, 1-methoxy-2-propyl acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (5-10%).

Gallon Weight:	8.16	Boiling Range:	259-428
% Solids by Weight:	27.46	H: 2 F: 3 R: 0	
% Solids by Volume:	27.80	Flash Point:	70°F
V.O.C.:	5.92 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray SB-961-2 SLM FINE ALUMINIUM

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, 1-methoxy-2-propyl acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (1-5%).

Gallon Weight:	8.12	Boiling Range:	259-428
% Solids by Weight:	48.10	H: 2 F: 3 R: 0	
% Solids by Volume:	35.26	Flash Point:	70°F
V.O.C.:	4.83 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray SB-962-2 SLM MEDIUM ALUMINIUM

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, 1-methoxy-2-propyl acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (1-5%).

Gallon Weight:	8.16	Boiling Range:	259-428
% Solids by Weight:	47.50	H: 2 F: 3 R: 0	
% Solids by Volume:	36.16	Flash Point:	70°F
V.O.C:	4.78 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray SB-967-2 SLM COARSE ALUMINIUM

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, 1-methoxy-2-propyl acetate, Xylene (5-10%), Cellulose Acetate Butyrate (5-10%), Aluminium (1-5%).

Gallon Weight:	8.14	Boiling Range:	259-428
% Solids by Weight:	47.60	H: 2 F: 3 R: 0	
% Solids by Volume:	35.80	Flash Point:	70°F
V.O.C:	4.79 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-780-2 PEARL WHITE

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, thermoplastic acrylic resin, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), titanium oxide.

Gallon Weight:	8.21	Boiling Range:	259-368
% Solids by Weight:	27.29	H: 2 F: 3 R: 0	
% Solids by Volume:	22.23	Flash Point:	77°F
V.O.C:	5.97 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-781-2 FINE PEARL WHITE

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), titanium oxide.

Gallon Weight:	8.23	Boiling Range:	259-368
% Solids by Weight:	27.47	H: 2 F: 3 R: 0	
% Solids by Volume:	22.66	Flash Point:	70°F
V.O.C:	5.97 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-782-2 PEARL BLUE

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, thermoplastic acrylic resin, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), titanium oxide.

Gallon Weight:	8.23	Boiling Range:	259-368
% Solids by Weight:	26.61	H: 2 F: 3 R: 0	
% Solids by Volume:	22.43	Flash Point:	77°F
V.O.C:	6.04 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-783-2 RED PEARL

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, thermoplastic acrylic resin, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), Iron Oxide (5-10%).

Gallon Weight:	8.20	Boiling Range:	259-368
% Solids by Weight:	27.20	H: 2 F: 3 R: 0	
% Solids by Volume:	22.15	Flash Point:	77°F
V.O.C:	5.97 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-784-2 PEARL GOLD

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), .

Gallon Weight:	8.36	Boiling Range:	259-368
% Solids by Weight:	29.20	H: 2 F: 3 R: 0	
% Solids by Volume:	22.24	Flash Point:	77°F
V.O.C:	5.92 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-785-2 COPPER PEARL

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), Iron Oxide (5-10%)

Gallon Weight:	8.26	Boiling Range:	259-368
% Solids by Weight:	28.33	H: 2 F: 3 R: 0	
% Solids by Volume:	22.42	Flash Point:	77°F
V.O.C:	5.92 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-786-2 PEARL WHITE ULTRAFINE

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%).

Gallon Weight:	8.25	Boiling Range:	259-368
% Solids by Weight:	28.73	H: 2 F: 3 R: 0	
% Solids by Volume:	22.50	Flash Point:	77°F
V.O.C:	5.91 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-787-2 PEARL RED FINE

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), Rutile (5-10%).

Gallon Weight:	8.28	Boiling Range:	259-368
% Solids by Weight:	28.63	H: 2 F: 3 R: 0	
% Solids by Volume:	22.25	Flash Point:	77°F
V.O.C:	5.91 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-788-2 RUSSET PEARL FINE

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), Iron Oxide (5-10%), .

Gallon Weight:	8.30	Boiling Range:	259-368
% Solids by Weight:	28.88	H: 2 F: 3 R: 0	
% Solids by Volume:	22.05	Flash Point:	77°F
V.O.C:	5.91 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-789-2 PEARL BLUE FINE

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), tin oxide, rutile.

Gallon Weight:	8.26	Boiling Range:	259-368
% Solids by Weight:	28.46	H: 2 F: 3 R: 0	
% Solids by Volume:	22.42	Flash Point:	77°F
V.O.C.:	5.91 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-790-2 PEARL VIOLET MEDIUM

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), titanium oxide.

Gallon Weight:	8.26	Boiling Range:	259-368
% Solids by Weight:	28.46	H: 2 F: 3 R: 0	
% Solids by Volume:	22.42	Flash Point:	77°F
V.O.C.:	5.91 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-791-2 PEARL GREEN MEDIUM

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), rutile, .

Gallon Weight:	8.27	Boiling Range:	259-368
% Solids by Weight:	28.54	H: 2 F: 3 R: 0	
% Solids by Volume:	22.30	Flash Point:	70°F
V.O.C.:	5.91 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-792-2 H.S. BLUE FROST

Hydroxy Acrylic Resin A, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Mica (5-10%), titanium oxide.

Gallon Weight:	8.37	Boiling Range:	259-368
% Solids by Weight:	28.08	H: 2 F: 3 R: 0	
% Solids by Volume:	20.30	Flash Point:	79°F
V.O.C.:	6.02 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-793-2 GRAPHITE FLAKE

Hydroxy Acrylic Resin A, thermoplastic acrylic resin, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Graphite (1-5%).

Gallon Weight:	7.88	Boiling Range:	259-368
% Solids by Weight:	30.50	H: 2 F: 3 R: 0	
% Solids by Volume:	23.07	Flash Point:	77°F
V.O.C.:	5.78 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PB-794-2 GOLD FLASH

Hydroxy Acrylic Resin A, thermoplastic acrylic resin, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Iron Oxide (1-5%), Aluminium (5-10%)

Gallon Weight:	8.10	Boiling Range:	259-368
% Solids by Weight:	27.83	H: 2 F: 3 R: 0	
% Solids by Volume:	23.39	Flash Point:	77°F
V.O.C.:	5.89 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PSE-1001-18 CRYSTAL SILVER

Hydroxy Acrylic Resin A, thermoplastic acrylic resin, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%).

Gallon Weight:	8.57	Boiling Range:	259-368
% Solids by Weight:	32.83	H: 2 F: 3 R: 0	
% Solids by Volume:	30.39	Flash Point:	77°F
V.O.C.:	5.82 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PSE-1002-18 SUNBEAM GOLD

Hydroxy Acrylic Resin A, thermoplastic acrylic resin, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%).

Gallon Weight:	8.57	Boiling Range:	259-368
% Solids by Weight:	32.63	H: 2 F: 3 R: 0	
% Solids by Volume:	29.39	Flash Point:	77°F
V.O.C.:	5.82 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray PSE-1003-18 RADIANT RED

Hydroxy Acrylic Resin A, thermoplastic acrylic resin, N – Butyl Acetate, Xylene (5-10%), solvent naphtha (petroleum), light aromatic, 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%).

Gallon Weight:	8.57	Boiling Range:	259-368
% Solids by Weight:	32.40	H: 2 F: 3 R: 0	
% Solids by Volume:	29.99	Flash Point:	77°F
V.O.C.:	5.82 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray VB-602-2 BRIGHT MAROON V.H.S.

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), C.I Pigment Red 224 (5-10%)

Gallon Weight:	8.25	Boiling Range:	259-418
% Solids by Weight:	44.25	H: 2 F: 3 R: 0	
% Solids by Volume:	39.79	Flash Point:	70°F
V.O.C.:	4.23 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray VB-604-2 PALE YELLOW

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), bismuth vanadium oxide (5-10%)

Gallon Weight:	9.38	Boiling Range:	259-418
% Solids by Weight:	54.64	H: 2 F: 3 R: 0	
% Solids by Volume:	40.85	Flash Point:	70°F
V.O.C.:	4.28 lb gal	OSHA Storage:	1B

Product Code: Pro-Spray VB-606-2 ORANGE RED

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), monoazo orange (10-20%).
Gallon Weight: 8.30 Boiling Range: 259-418
% Solids by Weight: 48.64 H: 2 F: 3 R: 0
% Solids by Volume: 42.70 Flash Point: 70°F
V.O.C: 4.09 lb gal OSHA Storage: 1B

Product Code: Pro-Spray VB-618-2 YELLOW

Hydroxy Acrylic Resin A, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (10%), yellow benzimidazolone (5-10%).
Gallon Weight: 8.46 Boiling Range: 259-418
% Solids by Weight: 48.64 H: 2 F: 3 R: 0
% Solids by Volume: 42.75 Flash Point: 70°F
V.O.C: 4.09 lb gal OSHA Storage: 1B

Product Code: Pro-Spray VB-620-2 H.S. RED VIOLET

Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, ethyl benzene, Xylene (10%), Quinacridone (10-20%)
Gallon Weight: 8.36 Boiling Range: 259-368
% Solids by Weight: 51.08 H: 2 F: 3 R: 0
% Solids by Volume: 43.39 Flash Point: 82°F
V.O.C: 4.09 lb gal OSHA Storage: 1B

Product Code: Pro-Spray VB-624-2 H.S. SPEED RED

Hydroxy Acrylic Resin B, Cellulose Acetate Butyrate (5-10%), 1-methoxy-2-propyl acetate, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, ethyl benzene, Xylene (10%), Pigment Red 254 (10-20%).
Gallon Weight: 8.65 Boiling Range: 259-368
% Solids by Weight: 52.79 H: 2 F: 3 R: 0
% Solids by Volume: 44.31 Flash Point: 82°F
V.O.C: 4.09 lb gal OSHA Storage: 1B

Product Code: Pro-Spray 400-3 H.S PLUS SUPER WHITE

Hydroxy Acrylic Resin C, Polyester Resin A, N – Butyl Acetate, Methyl isoamyl Ketone, Titanium Dioxide (20-30%), silica, aluminium hydroxide.
Gallon Weight: 12.20 Boiling Range: 259-418
% Solids by Weight: 79.00 H: 2 F: 3 R: 0
% Solids by Volume: 61.80 Flash Point: 70°F
V.O.C: 2.48 lb gal OSHA Storage: 1B

Product Code: Pro-Spray SCB-673-3 SINGLE LAYER ADJUSTER

Acrylic Resin A, Acrylic Resin B, n -Butyl Acetate, Xylene (2%), Solvent naphtha (petroleum) light aromatic.
Gallon Weight: 8.01 Boiling Range: 259-418
% Solids by Weight: 50.00 H: 2 F: 3 R: 0
% Solids by Volume: 42.42 Flash Point: 77°F
V.O.C: 4.73 lb gal OSHA Storage: 1B

Product Code: Pro-Spray SCB-408-3 SINGLE LAYER BINDER

Acrylic Resin A, Acrylic Resin B, n -Butyl Acetate, Xylene (2%), Solvent naphtha (petroleum) light aromatic.
Gallon Weight: 8.01 Boiling Range: 259-418
% Solids by Weight: 50.00 H: 2 F: 3 R: 0
% Solids by Volume: 42.42 Flash Point: 77°F
V.O.C: 4.73 lb gal OSHA Storage: 1B

(Product Code: Pro-Spray BCB-005-3 BASECOAT FLIP CONTROL

Acrylic Polymer A, Polyester Polymer A, Xylene (20-30%), n - Butyl Acetate, 1-Methoxy-2-propyl acetate, Cellulose Acetate Butyrate, Wax Dispersion.
Gallon Weight: 7.59 Boiling Range 259-295
% Solids by Weight: 16.30 H: 2 F: 3 R: 0
% Solids by Volume: 18.43 Flash Point 70°F
V.O.C: 6.34 lb gal OSHA Storage: 1B

(Product Code: Pro-Spray BCB-600-3 BASECOAT BALANCER

Acrylic Polymer A, Polyester Polymer A, Xylene (20-30%), n - Butyl Acetate, 1-Methoxy-2-propyl acetate, Cellulose Acetate Butyrate, Wax Dispersion.
Gallon Weight: 7.59 Boiling Range 259-295
% Solids by Weight: 16.30 H: 2 F: 3 R: 0
% Solids by Volume: 18.43 Flash Point 70°F
V.O.C: 6.34 lb gal OSHA Storage: 1B

Product Code: Pro-Spray BCB-825-3 BASECOAT FLIP CONTROL H.S.

Hydroxy Acrylic Resin, Acrylic Resin, Solvent naphtha (petroleum) light aromatic, Xylene (10-20%), n - Butyl Acetate, 1-Methoxy-2-propyl acetate, Wax Dispersion.
Gallon Weight: 7.71 Boiling Range 259-418
% Solids by Weight: 30.78 H: F: R:
% Solids by Volume: 25.78 Flash Point: 70°F
V.O.C: 6.25 lb gal OSHA Storage: 1B

(Product Code: Pro-Spray SCBC-574-3 SOLID COLOR BASECOAT CONVERTER

Acrylic Polymer A, Xylene (5-10%), n - Butyl Acetate, 1-Methoxy-2-propyl acetate, Cellulose Acetate Butyrate, Silica,
Gallon Weight: 8.25 Boiling Range: 176-295
% Solids by Weight: 30.64 H: 2 F: 3 R: 0
% Solids by Volume: 25.64 Flash Point 70°F
V.O.C: 5.74 lb gal OSHA Storage: 1B

Product Code: Pro-Spray A-380-2 MATTING AGENT

Hydroxy Acrylic Resin A, Hydroxy Acrylic Resin B, solvent naphtha (petroleum), light aromatic, ethyl benzene, N – Butyl Acetate, Xylene (5-10%), Silica (10-20%)
Gallon Weight: 8.67 Boiling Range: 259-418
% Solids by Weight: 51.32 H: 2 F: 3 R: 0
% Solids by Volume: 42.22 Flash Point: 70°F
V.O.C: 4.22 lb gal OSHA Storage: 1B

Product Code: Pro-Spray P-526-2 TEXTURE ADDITIVE FINE

Hydroxy Acrylic Resin A, Polyester Resin, nylon, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (10%).
Gallon Weight: 8.58 Boiling Range: 259-418
% Solids by Weight: 60.00 H: 2 F: 3 R: 0
% Solids by Volume: 59.00 Flash Point: 73°F
V.O.C: 3.33 lb gal OSHA Storage: 1B

Product Code: Pro-Spray P-528-2 TEXTURE ADDITIVE COARSE

Hydroxy Acrylic Resin A, Polyester Resin, nylon, solvent naphtha (petroleum), light aromatic, N – Butyl Acetate, Xylene (10%).
Gallon Weight: 6.49 Boiling Range: 259-418
% Solids by Weight: 60.00 H: 2 F: 3 R: 0
% Solids by Volume: 60.00 Flash Point: 73°F
V.O.C: 3.33 lb gal OSHA Storage: 1B

Product Code: Pro-Spray P-2020-2 PLASTICIZING ADDITIVE

Polyester Resin, n -Butyl Acetate, Xylene (2%), Solvent naphtha (petroleum) light aromatic.
Gallon Weight: 8.50 Boiling Range: 259-418
% Solids by Weight: 60.00 H: 2 F: 3 R: 0
% Solids by Volume: 54.00 Flash Point: 75°F
V.O.C: 3.28 lb gal OSHA Storage: 1B

Product Code: Pro-Spray EBB-20-3 ENGINE BAY BINDER

Hydroxy acrylic Polymer A, n – Butyl Acetate, Xylene (5%), Titanium Dioxide, calcium carbonate, Barium sulfate.
Gallon Weight: 13.15 Solvent Density: heavier than air
% Solids by Weight: 77.00 H: 2 F: 3 R: 0
% Solids by Volume: 56.85 Flash Point: 70°F
V.O.C: 3.02 lb gal OSHA Storage: 1B

Product Code: Pro-Spray EBA-50-3 ENGINE BAY ADJUSTER

Hydroxy acrylic Polymer A, n – Butyl Acetate, Xylene (5%), Titanium Dioxide, calcium carbonate, Barium sulfate.
Gallon Weight: 11.23 Solvent Density: heavier than air
% Solids by Weight: 70.00 H: 2 F: 3 R: 0
% Solids by Volume: 44.85 Flash Point: 70°F
V.O.C: 3.40 lb gal OSHA Storage: 1B

Product Code: Pro-Spray CSS-3500-3 COMPLIANT SINGLE LAYER BINDER

Acrylic Resin, n -Butyl Acetate, 2-Butoxyethyl Acetate, methyl isoamyl Ketone, Acetone (15.5%).
Gallon Weight: 8.23 Boiling Range: 259-418
% Solids by Weight: 60.00 H: 2 F: 3 R: 0
% Solids by Volume: 57.42 Flash Point: 77°F
V.O.C: 3.29 lb gal OSHA Storage: 1B
V.O.C less Exempt 2.56 lb gal

Product Code: Pro-Spray CSS-3510-3 COMPLIANT SINGLE JET BLACK

Hydroxy acrylic Polymer A, Acrylic Resin, n -Butyl Acetate, methyl isoamyl Ketone, Carbon Black (1-5%).
Gallon Weight: 8.35 Boiling Range: 259-418
% Solids by Weight: 55.00 H: 2 F: 3 R: 0
% Solids by Volume: 50.42 Flash Point: 77°F
V.O.C: 3.75 lb gal OSHA Storage: 1B
V.O.C less Exempt 3.75 lb gal

Product Code: Pro-Spray P-451-2, P-451-3 BASECOAT JET BLACK

Hydroxy Acrylic Resin A, thermoplastic acrylic resin, N – Butyl Acetate, Xylene (5-10%), 1-methoxy-2-propyl acetate, ethyl benzene, Cellulose Acetate Butyrate (5-10%), Carbon Black (1-5%).
Gallon Weight: 7.84 Boiling Range: 259-418
% Solids by Weight: 29.40 H: 2 F: 3 R: 0
% Solids by Volume: 26.50 Flash Point: 70°F
V.O.C: 5.53 lb gal OSHA Storage: 1B