

TECHNICAL DATA SHEET

USC Aerosol Under Coating

TECHNICAL CALLS: 1-855-746-4872 (1-855-RING USC)



DESCRIPTION: USC Under Coating is An autobody undercoating for application to the undercarriage for rust protection and sound deadening. Asphalt base undercoating remains pliable and resists temperature extremes. Sprays evenly and dries completely to a smooth consistency. Does not sag and dries quickly.

PART NUMBER: 51333



PRODUCT USES:

- Panel & fender undersides
- Hoods & decks
- Trunk interiors
- Section repairs
- Weld joints
- Rust holes
- All chassis parts

Packaging:

UPC Code	037307513339
Cans per case	12
Shipping weight per case	19.6 lbs.
Container	20 fluid ounce can
Label weight	18 ounces (511 grams)
Shipping Classification	Consumer Commodity ORM-D UN 1950
Hazard Class	2.1

Properties:

Flammability	"Extremely Flammable"
Flash point	-4o F
Specific Gravity	0.80
Solids Content	~40%
VOC content	~29%, cannot exceed 40%
MIR value	~0.30
HAPs content	4%
Storage Temperature	40-90F
Application Temperature	50-100F
Durability	Very Good
Abrasion Resistance	Very Good
Heat Resistance	300o F
Gasoline Resistance	No
Resin System	Petroleum Asphalt
Shelf life	Guaranteed for 2 years

Dry Time*:

To touch	10 minutes
To handle	6 hours

*At 720 F, 50% humidity,
1.5 mil thickness

**Curing/Recoat time is extended with
multiple coats and excessively thick
coats**

Gloss*:

Low Lustre, 15-25

*as measured on a 600 gloss meter